

Amendments to the Specification:

Please replace paragraph [0081], Table 1, with the following rewritten paragraph:

[0081]

[Table 1]

Table 1	(Sheet)			Ex. 1 (Blank 1)			Ex. 2 (Blank 2)			Ex. 3 (Blank 3)			Ex. 4 (Blank 4)			Ex. 5 (Blank 5)		
	phr	wt%	vol%	phr	wt%	vol%	phr	wt%	vol%	phr	wt%	vol%	phr	wt%	vol%	phr	wt%	vol%
Inorganic Colorant		100	16.67		100	16.7		100	16.7		100	16.7		100	16.7		100	16.7
Resin		6	6		4.5	4.5		4.5	4.5		6	6		6	6		9	9
Plasticizer	50	3	3	140	6.3	6.3	250	11.3	11.3	80	4.8	4.8	100	6	6	30	2.7	2.7
Organic Binder Component		9	9		10.8	10.8		15.8	15.8		10.8	10.8		12	12		11.7	11.7
Inorganic Colorant Ratio of Resin and Plasticizer		9	54		10.8	64.8		15.8	94.5		10.8	64.8		12	72		11.7	70.2
Difference of Inorganic Colorant Ratio (Blank) - (Sheet)					1.8	10.8		6.75	40.5		1.8	10.8		3	18		2.7	16.2
				Ethyl Cellulose			Ethyl Cellulose			Butyral			Butyral			Butyral		

Property

Stacking Property of Ceramic Green Multilayer Chip	No Unsticking between Layers	No Unsticking between Layers	No Unsticking between Layers	No Unsticking between Layers
Cutting Yield 9%	100	100	100	100
Internal Defect Rate % of Ceramic Capacitor Samples	0	0	0	0
Interlayer Thickness μm	22	2.1	2.2	2.2